


BPA Testing – Comparison of Aluminum Water Bottles

Bottle Photo	Brand of Bottle	Retailer where purchased	Country where manufactured	BPA test result (liner)	Date & Laboratory of testing
	SIGG	Whole Foods Market	Switzerland	No BPA detected	July 2009 @ SQTS *
	No name brand	The Container Store	China	20 µg/dm²	July 2009 @ SQTS *
	Pottery Barn®	Pottery Barn	China	6 µg/dm²	July 2009 @ SQTS *
	Pottery Barn®	Pottery Barn	China	90 µg/dm²	July 2009 @ SQTS *

	Paper Chase	Borders	China	13µg/dm²	July 2009 @ SQTS *
	Paper Chase	Borders	China	2 µg/dm²	July 2009 @ SQTS *
	No name brand	Old Navy	China	70 µg/dm²	July 2009 @ SQTS *
	No name brand	Old Navy	China	22 µg/dm²	July 2009 @ SQTS *

- *SQTS** - Swiss Quality Testing Services, 8953 Dietlikon, Switzerland
- testing according worst-case-model (acceptable according to 2002/72/EG) and according EN 14350-2:2004
 - Method of extraction and HPLC-Analysis according to prCEN/TSEN 13130-13
 - Extraction: cold extraction by motion during 1 hour | evaporation | concentrate | dissolving | HPLC-fluorescence analysis